



Recommended Installation Specification | 10 Pedestrian & light vehicular applications

Concrete Base

Mortar Laying Course

30mm to 40mm thick

Mortar should consist of freshly mixed, moist 1:3 cement-sand mortar (proportions by volume) or 1:3 lime:sand mortar (proportions by volume), using sand complying with Australian Standards.

Alternatively - Pre mixed concrete (tile mix) supplied by a concrete supplier with 300kg cement per m³ of sand delivered by agitator concrete truck at nil-slump.

Joints

5 to 10mm wide

1:4 cement-sand (proportions by volume) using sand complying with Australian Standards

NOTE: Paver must fully adhere to the concrete slab. No moisture should be retained beneath paver.

Crushed Rock Base (compacted 95%)

Sand Laying Course

30mm thick

Sand should be free of salts likely to cause efflorescence and should comply with Australian standards

Sand must be dry when laying

Adequate provisions for draining the bedding sand shall be provided

Joints

3 to 5mm wide

Jointing sand should be dry

Sand shall be free of salts likely to cause efflorescence and should comply with Australian standards